



## Dimension plank

<b>LENGTH</b>	23-2/3" (600 mm)
<b>WIDTH</b>	4-3/4" (120 mm)
<b>TOTAL THICKNESS</b>	9/16" (14 mm)

## Dimension box

<b>BOX LENGTH</b>	24" ( 610 mm)
<b>BOX WIDTH</b>	11" (280 mm)
<b>BOX THICKNESS</b>	7" (180 mm)
<b>BOX WEIGHT</b>	51 lb
<b>LAYERS/BOX</b>	24
<b>SQFT/BOX</b>	20.88 sqft

## Dimension pallet

<b>PALLET LENGTH</b>	39-1/3" (1000 mm)
<b>PALLET WIDTH</b>	47-1/4" (1200 mm)
<b>PALLET HEIGHT</b>	41-1/3" (1050 mm)
<b>PALLET WEIGHT</b>	2090 lb
<b>BOX/PALLET</b>	40
<b>SQFT/PALLET</b>	837.00 sqft

## FEATURES

### Top layer

<b>WOOD TYPE</b>	Oak
<b>LATIN NAME</b>	Quercus Robur
<b>GRADE</b>	PRIME
<b>CONSTRUCTION</b>	3-layer
<b>BEVEL</b>	Micro bevel 4 sides (0.5 mm)
<b>SURFACE STRUCTURE</b>	Brushed

### Composition of the support

<b>SUPPORT TYPE</b>	Engineered
<b>BASE OF THE SUPPORT</b>	Plywood

### Placement

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove	· Light household use	Yes
	· Moderate commercial use	<b>RE-SANDABLE</b>
	· Normal commercial use	Yes
	· Normal household use	
	· Intensive commercial use	

### TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	CARB PH2	CARB PH2
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m <sup>2</sup> k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

### CERTIFICATION



EN 14342

