



## Dimension plank

<b>LENGTH</b>	92 1/2" (2350 mm) RL
<b>WIDTH</b>	9 1/2" (242 mm)
<b>TOTAL THICKNESS</b>	5/8" (15 mm)

## Dimension box

<b>BOX LENGTH</b>	93" (2362 mm)
<b>BOX WIDTH</b>	9 3/4" (248 mm)
<b>BOX THICKNESS</b>	2 1/2" (64 mm)
<b>BOX WEIGHT</b>	45 lb
<b>LAYERS/BOX</b>	4
<b>SQFT/BOX</b>	24.48 sqft

## Dimension pallet

<b>PALLET LENGTH</b>	93 2/3" (2380 mm)
<b>PALLET WIDTH</b>	38 1/2" (980 mm)
<b>PALLET HEIGHT</b>	41 1/2" (1055 mm)
<b>PALLET WEIGHT</b>	3375 lb
<b>BOX/PALLET</b>	75
<b>SQFT/PALLET</b>	1836.00 sqft

## FEATURES

## Top layer

<b>WOOD TYPE</b>	Oak
<b>LATIN NAME</b>	Quercus Robur
<b>GRADE</b>	CLASSIC
<b>CONSTRUCTION</b>	2-layer
<b>BEVEL</b>	Micro bevel 2 long sides (0,5 mm)
<b>SURFACE STRUCTURE</b>	Brushed

## Composition of the support

<b>SUPPORT TYPE</b>	Engineered
<b>BASE OF THE SUPPORT</b>	Plywood

## Placement

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove	· Light household use	Yes
	· Moderate commercial use	<b>RE-SANDABLE</b>
	· Normal commercial use	Yes
	· Normal household use	
	· Intensive commercial use	

### TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	CARB PH2	CARB PH2
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m <sup>2</sup> k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

### CERTIFICATION



EN 14342

